

International Independent Inspection &amp; Testing Company

P.O. Box 2209, Plot No. TP/010305, Techno Park, Dubai - United Arab Emirates, Tel. +971 4 8867400

Operation: Fax. +971 4 8867401, Email: operations@geochem.ae, Laboratory: Fax. +971 4 8867402, E-mail: laboratory@geochem.ae

ISO 9001:2008 CERTIFIED COMPANY

www.geochem.ae

Certificate No : LC-16/C820-E/AIS  
Date : 29/11/2016

ORIGINAL

## Certificate of Quality and Quantity

Description of Goods	: 198 BAGS BITUMEN 60/70
Packing	: 9 X 20' DC CONTAINERS
Total Gross Weight	: 200,320 KGS
Total Net Weight	: 207,250 KGS
Shipper	: GLOBAL INFINITY GENERAL TRADING FZE DUBAI - UAE
Consignee	: SINGAPORE
Notify Party	: SAME AS CONSIGNEE
Vessel Name & Voy Number	: INTER SYDNEY WID22N
Port of Discharge	: DOUALA
B/L No. and Date	: AYY0105839 DATE:28.11.2016
H.S CODE	: 2713/2000

### Quality

We hereby certify that based on analysis result of samples drawn during the entire loading period and tested the results found (Lab report No: AIS/LAB/BAB/016-10-47) as follows:

Test Items	Methods	Unit	Result
Penetration 25 °C	ASTM D 5	0.1mm	68
Flash Point	ASTM D 92	°C	324
Solubility in TCE	ASTM D 4	%Wt	99.8
Specific Gravity @ 25 °C	ASTM D 70	-	1.0302
Ductility @ 25 °C	ASTM D 113	Cm	>100
Spot Test	A.A.S.H.T.O 102	-	NEG
Softening Point	ASTM D 36	°C	49.2
Thin Film Oven Test	ASTM D 1754		
Loss on Heating	ASTM D 6	%Wt	0.06
Drop In Penetration After Heating	ASTM D 5	%	14.2



.../2